



洛阳建龙微纳新材料股份有限公司  
Luoyang Jalon Micro-nano New Materials Co., Ltd.

Add: Junmin Rd. Ind. Cluster District, Yanshi, Henan, 471900, China

Tel: +86-379-6989 5719

Fax: +86-379-6989 5717

## ACTIVIATED ALUMINA

**Activated alumina** is used for deep drying of gas or liquid phase of petrochemicals and adsorption drying by automatic instruments.

### Technical Specification

Property	Unit	JLAA-2	JLAA-4	JLAA-3I	JLAA-3II	JLAA-5	JLAA-7	JLAA-9	Note
Diameter	mm	1.0-2.2	3.0-5.0	2.0-3.0	3.0-4.0	4.0-6.0	6.0-8.0	8.0-10.0	
Bulk density	g/ml	≥0.70	≥0.70	≥0.70	≥0.70	≥0.65	≥0.60	≥0.60	Tapped
Crush strength	N	≥25	≥120	≥50	≥80	≥150	≥220	≥280	Average 25 beads
Static water adsorption	%wt	≥17							RH60%, 25°C
Loss on attrition	%wt	≤0.30							-
LOI	%wt	<8.00							800°C, 2hours

### Packing:

55 gallon air-tight iron drum;

Supersack;

Carton.

**ISO9001, ISO14001 and OHSAS18001 certified zeolite manufacturer**